




Fixit 777

Final render extra white

Areas of use: Fixit 777 is a mineral finish coat for cement, lime and gypsum-based substrates as well as for ETIC systems for outdoor and indoor use. The surface must be clean, dry and stable. The prior application of Fixit 475 Primer for mineral plasters is recommended.

- Properties:**
- Mineral-based and biocide-free
 - Extra white
 - Diverse structures possible
 - Weather resistant
 - On gypsum, limestone and cement substrates
 - Range of grain sizes
 - ECO certified

Application procedure:



Technical data					
Item no.	2000958751	2000634655	2000663005	2000663006	2000958752
Packaging type	☐				
Unit per pallet	40 unit/pal.				
Quantity per unit	25 kg/unit				
Granulation	1 mm	1.5 mm	2 mm	3 mm	4 mm
Dashed	Full abrasion				
Consumption	approx. 1,8 kg/m ²	2–2,2 kg/m ²	2,5–2,9 kg/m ²	3,3–4,0 kg/m ²	5–5,3 kg/m ²
Application time	approx. 90 min				



Item no.	2000958754	2000958756	2000958757	2000958758	2000958759
Packaging type	☐				
Unit per pallet	40 unit/pal.				
Quantity per unit	25 kg/unit				
Granulation	4 - 6 mm	5 mm	1.5 mm	2 mm	3 mm
Dashed	Full abrasion	Full abrasion	Groove	Groove	Groove
Consumption	5,2–5,5 kg/m ²	approx. 5,5 kg/m ²	approx. 2 kg/m ²	2,5–3 kg/m ²	
Application time	approx. 90 min				

Item no.	2000958760		2000958761	
Packaging type	☐			
Unit per pallet	40 unit/pal.			
Quantity per unit	25 kg/unit			
Granulation	5 mm		0.5 mm	
Dashed	Groove			
Consumption	approx. 4,9 kg/m ²		1,5–2 kg/m ²	
Application time	approx. 90 min			



Fixit 777

Final render extra white

Composition:	<ul style="list-style-type: none"> • Binder: White lime, white cement • Aggregates: Marble sand • Additives: Water retention agents, air entraining agents, bonding agents, water repellent medium
Basics:	The general rules of building construction must be observed, in addition to the current notes published by the «Swiss Association of Painters and Plasterers SMGV», the SIA 242 «Plaster and drywall work», the SIA 243 «Plastered exterior thermal insulation» and the information in this technical data sheet.
Application procedure:	Fixit 775 is mixed with clean water. On substrates which absorb water poorly, adhesion must be improved by adding to the mixing water approximately 0,5 L of Fixit 497 Plaster and Mortar Emulsion per sack .
Post-application treatment:	The freshly applied render should be protected from exposure to bad weather and direct sunshine. Provide shade, additional humidification, protection from driving rain and hail etc. as necessary.
Storage:	Store in a dry place on wooden battens. Storage life min. 12 months. Binding properties may be affected if stored for longer.
Certificates:	
Further notes:	
Important note:	<p>Do not use if air or ground temperature is below +5 °C.</p> <p>Dry construction boards and gypsum boards must be completely coated with a filler layer or with Fixit 475 Primer for Mineral-based Final Renderings before applying the final rendering. On all other substrates, priming is recommended beforehand.</p> <p>When negative texture is being worked with a mineral finish coat using a plastic finishing trowel, then the trowel MUST be carefully selected in order to achieve the necessary structure.</p> <p>For finely textured plaster surfaces (grain size below 1mm) the substrate must be of quality level Q3.</p> <p>Drying</p> <p>The setting time of Fixit 777 depends on the temperature and relative humidity of the surroundings. Low temperatures and/or high humidity delay the drying process. After about 10 days at + 20° C air and substrate temperature, and 65 % relative humidity, painting may begin. Basically, the Fixit 777 may only be painted after sufficient time has elapsed to allow complete carbonation to occur.</p>
General provisions:	This technical information sheet replaces all previous versions of the information sheet for this product. The details in this technical information sheet were drawn up carefully and conscientiously based on the current state of knowledge and experience and refer to the usual purpose of use. The information is provided without any warranties regarding accuracy and completeness and any and all liability is excluded. It also does not establish any contractual legal relationship with or subsidiary obligation of Fixit AG. Customers and users are personally responsible for checking that the products are suitable for the intended purpose of use. The latest versions of our technical information sheets are available on our website or can be ordered from the competent branch.