



GRUNT RENOWCYJNY NA RYSY 906

Silicate primer for filling cracks

Areas of application: Ready-to-use primer based on potassium water glass with quartz filler. Thanks to the quartz fillers, it is suitable as a filler for small stable shrinkage cracks on walls made with cement-lime or lime plasters. It can also be used as a bonding layer on various old substrates before applying the final mineral coating (e.g., stucco) and for creating a uniform structure under paint coatings. Reinforces the groundwork, limits and evens out its absorbency without hindering its vapor-permeability. Indoor and outdoor use

- Properties:**
- Waterproof
 - Frost-resistant
 - Vapor-permeable
 - With quartz addition
 - Covers cracks
 - High grip
 - High openness to diffusion

Application procedure:



Technical data	
Packaging type	
Quantity per unit	8 kg/unit
Unit per pallet	80 Pcs/pallet
Consumption	0.25 kg/m ²
Drying time	12 h

The product conforms to: • The product is not a construction product and does not require a reference document.

- Material base:**
- Quartz aggregate
 - Additives
 - Special binding agent
 - Potassium water glass

Surface: Absorbent and dusty substrates should be surface-strengthened using REMONT GRUNT 950 or appropriately diluted IMPREGNATION LIQUID 900. Signs of biological aggression should be eliminated using SEPTOBUD 1008. Cover all surfaces not intended for priming before the primer is applied.

Types of substrate:

Cement-lime plaster: Prime with REMONT GRUNT 950 or IMPREGNATION LIQUID 900 (diluted 1:2).

Gypsum plaster: Prime with REMONT GRUNT 950.

Cement-lime plaster: Prime with REMONT GRUNT 950.

Gypsum plasterboards: Prime with REMONT GRUNT 950.

Concrete: Prime with REMONT GRUNT 950 or IMPREGNATION LIQUID 900 (diluted 1:2).

Old thin-layer mineral and dispersion plasters:

Fresh mineral plaster: Apply directly (after a minimum of 14 days of plaster drying)

Preparation: The product is ready for use. Depending on the application technique and the size of the cracks, it can be diluted with water up to a maximum ratio of 1:2. Can be tinted to match the color of the plaster mass.

Application procedure: Primer, apply with a roller, brush or using spray application. Protect against frost, precipitation, excessive drying during the execution of works and drying. Do not apply scaffolding covers. High humidity and low air temperatures significantly increase the drying time of the product.



GRUNT RENOWCYJNY NA RYSY 906

Silicate primer for filling cracks

Application conditions:	<p>Apply at temperatures from +5 °C to +25 °C, these temperatures apply to air, bed and product. All substrates shall be bearing, compact, stable, even and clean</p> <p>All substrates must have adequate load-bearing capacity, solid and compact structure and be cleaned of dust, grease, lubricants, release agents, paint residues, etc. Unstable coatings and coatings with insufficient adhesion must be removed. Oily and lubricated surfaces should be washed with detergent, infected with mold, moss, algae should be covered with SEPTOBUD 1008 and then washed under high pressure or mechanically removed.</p>
Storage:	<p>The mortar can be stored for up to 12 months from production date in sealed packaging and at temperatures, ranging from +5 °C to +25 °C. The storage area shall be kept out of the reach of children, protected against direct sunlight and located far from heat sources and naked flames. It can be transported by any means of transport, at a temperature not lower than +5 °C. It is not subject to ADR provisions.</p>
General information:	<p>This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing.</p>
