



Fixit 203

Finish coat with hydraulic lime


Areas of use: Fixit 203 is a paint-ready mineral-based finish coat for indoor and outdoor use and is ideal for replicating historical structured plasterwork. Hydraulic plasters are particularly suitable substrates. Older base coats with poor strength may be reinforced by pretreating with Fixit 493 mineral Base Coat Stabilizer.

Properties:

- Historic plaster surface imitation possible, with a range of application techniques
- Hydrophilic and therefore with very good capillary active and water vapour diffusion properties
- For both indoor and outdoor use
- ECO certified

Application procedure:



Technical data	
Item no.	2000578332
Packaging type	
Unit per pallet	40 unit/pal.
Quantity per unit	25 kg/unit
Granulation	0 - 1 mm
Water addition rate	5 - 6 l/bag
Consumption	approx. 1.3 kg/m ² /mm
Application time	90 - 120 min
Layer thickness	1 - 3 mm

Composition:

- Binding agent: hydraulic lime, white hydrated lime, white cement
- Aggregates: sand-lime with grain size 0 - 1 mm
- Additives: Water retention agents, air entraining agents

Basics: The general rules of building construction must be observed, in addition to the current notes published by the «Swiss Association of Painters and Plasterers SMGV», the recommendations SIA 242 «Rendering and Plastering» and the information in this technical data sheet.

Application procedure: Fixit 203 should be mixed with clean water by hand. Marble pit lime may be added to the mixing water to improve smoothness and increase the strength of the render. The substrate must be wetted in advance of application. The surface structure can be created using trowel strokes, jute-sack impressions, brush strokes, whitewash etc.

Post-application treatment: The freshly applied render should be protected from exposure to bad weather and direct sunshine. Provide shade, additional humidification, protection from driving rain and hail etc. as necessary.

Storage: Store in a dry place on wooden battens. Storage life min. 12 months. Binding properties may be affected if stored for longer.

Certificates:



Further notes:



Important note: Do not apply when the air or substrate temperature is below +5 °C or above +30 °C. Allow the plaster to adequately carbonate before applying paint coats. Exception: lime paint may be applied "wet-on-wet".



Fixit 203

Finish coat with hydraulic lime

General provisions:

This technical information sheet replaces all previous versions of the information sheet for this product. The details in this technical information sheet were drawn up carefully and conscientiously based on the current state of knowledge and experience and refer to the usual purpose of use. The information is provided without any warranties regarding accuracy and completeness and any and all liability is excluded. It also does not establish any contractual legal relationship with or subsidiary obligation of Fixit AG. Customers and users are personally responsible for checking that the products are suitable for the intended purpose of use. The latest versions of our technical information sheets are available on our website or can be ordered from the competent branch.