


## TECHNICAL DATA SHEET

---

### Turbo-WSA

Thermal insulation system on mineral wool with silicate plaster.



#### Areas of application

---

For the implementation of insulation systems in housing, public and industrial construction For new and modernized buildings. Particularly suitable for buildings in the vicinity of trees, water reservoirs and industrial agglomerations.

#### Surface

---

All substrates must have adequate load-bearing capacity, solid and compact structure and be cleaned of dust, grease, lubricants, release agents, paint residues, etc. Unstable coatings and coatings with insufficient adhesion must be removed. Oily and lubricated surfaces should be washed with detergent, infected with mold, moss, algae should be covered with SEPTOBUD 1008 and then washed under high pressure or mechanically removed.

Old paint coats Old plasters Silicate blocks Autoclaved aerated concrete elements Concrete and concrete blocks Bricks and ceramic CMUs Concrete, reinforced concrete clean and possibly prime with GRUNTOLIT-SG 302  
Incompatible Prime with GRUNTOLIT-W 301 or EXPERT 6  
Prime with GRUNTOLIT-SG 302 or EXPERT 5


#### Instructions

---

In the thermal insulation system, use mineral wool compliant with EN 13162, with a reaction to fire class A1, an apparent density of  $\leq 150 \text{ kg/m}^3$ , and minimum TR5. For lamella wool, use products with at least TR80. For thermal insulation systems, we recommend reinforcing meshes with a specific weight of  $> 145 \text{ g/m}^2$  and the following parameters: absolute tensile strength after ageing (N/mm):  $\geq 20$ ; relative residual strength after ageing compared to as-delivered strength (%):  $\geq 50$ . In thermal insulation systems, mechanical fixings with the following parameters are permitted: plate diameter of 60mm, plate stiffness (surface installation)  $\geq 0.3 \text{ kN/mm}$ , plate stiffness (recessed installation)  $\geq 0.6 \text{ kN/mm}$  Protect against frost, precipitation, excessive drying during the

#### Application procedure

---



## Turbo-WSA

Thermal insulation system on mineral wool with silicate plaster.

execution of works and drying. Do not apply scaffolding covers.

### General information

---

This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing.

All technical data listed in this product specification has been determined under laboratory conditions.

Acceptance of thermal insulation systems. The final acceptance of the insulation system should include checking the surface evenness and a visual inspection. The visual assessment of the external appearance of the render finishes should be carried out with the naked eye, under diffused light, from a distance of more than 3 m. We would like to point out that currently there are no official standards for the acceptance of thin-coat renders. Therefore, the guidelines provided by the Association for Thermal Insulation Systems – which brings together insulation system manufacturers and of which KREISEL is a member – should be followed. According to these guidelines, thin-coat textured and mosaic renders applied on insulation systems or on base coats should, in terms of tolerance control for surfaces and edges, be treated as category III renders. This should be specified in the construction contract. The permissible deviations from vertical for external edges of category III renders should not exceed: 2 mm per 1 m over the entire storey height – 10 mm over the entire building height – 30 mm. The permissible deviations from vertical for external render surfaces should not exceed: – over the entire building height – 30 mm.