



MULTI 102

Basic, frost-proof adhesive

Areas of application: Intended for applying wall and floor tiles on indoor and outdoor surfaces
Ideal for rigid, non-deforming and well-gripping groundworks.
For applying wall and floor tiles with absorbency >3% (ceramics and terracotta)

Properties:

- Waterproof
- Frost-resistant
- Economic
- For tiles and terracotta
- C1T class

Application procedure:



Technical data	
Item no.	3838
Packaging type	
Quantity per unit	20 kg/unit
Unit per pallet	64 unit/pal.
Colour	Grey
Granulation	0 - 0.5 mm
Consumption	1.4 kg/m ² /mm
Drying time	from 24 to 48 hours
Application time	2 h
Layer thickness	1 - 5 mm
Soluble chromium VI content	≤ 0.0002 %
Amount of water required	approx. 4.6 l/unit
Possibilities to enter	approx. 24 h
Groutable	after 48 hours
Adhesive group (EN 12004+A1)	C1 T
Adhesion to (Concrete)	≥ 0.5 MPa
Correction possibility	approx. 10 min
Adhesive open time	10 min

The product conforms to: • EN 12004+A1

Material base:

- Mineral fillers
- Modifying supplements
- Portland cement

Surface: Remove all mortars and unstable layers. Plasters and cement screeds must be at least 4 weeks old. Concrete surfaces must be at least 6 months old.
Level all groundwork irregularities with the 428 leveling grout. Irregular cement and concrete floor surfaces should be leveled with the RENOGRUNT 410, QUICK-SETTING SELF LEVELING GROUT 417 or EXPERS 419 self-leveling grout.



MULTI 102

Basic, frost-proof adhesive

Types of substrate:	<p>Concrete: Prime with CONTACT GRUNT 307</p> <p>Cement-lime plaster: Prime with GRUNTOLIT-B 300 or GRUNTOLIT-W 301 or EXPERT 6.</p> <p>Gypsum plaster: Prime with GRUNTOLIT-B 300 or GRUNTOLIT-W 301 or EXPERT 6.</p> <p>Cement screed: Prime with GRUNTOLIT-B 300 or GRUNTOLIT-W 301 or EXPERT 6.</p> <p>Autoclaved aerated concrete elements: Prime with GRUNTOLIT-B 300 or GRUNTOLIT-W 301 or EXPERT 6.</p> <p>Silicate blocks: Prime with GRUNTOLIT-B 300 or GRUNTOLIT-W 301 or EXPERT 6.</p>
Preparation:	<p>Pour the dry mix gradually to a container with a sufficient amount of clean, cool water. Mix manually or using a low-speed mixer to produce a homogeneous mass without lumps. Leave to mature for 5 minutes and mix again. The mass should be thick enough not to slide from a trowel when set at an angle.</p> <p>If there is a need to use a part of the packaging, the entire dry compound must be carefully stirred because during transport components could be separated.</p> <p>Do not mix the hardened grouting mixture again.</p>
Application procedure:	<p>Apply the prepared mortar onto the steel trowel and firmly spread a thin layer across the bed using the straight edge. The next step is to apply a thicker mortar layer and spread it using the notched edge of the trowel at an angle of 45-60 degrees to the bed. The area covered with the mortar should be adjusted to the tiles laying abilities not to exceed the open drying time of the adhesive. It can be verified by touching the grout with a finger, if no adhesion occurs, the open drying time was exceeded and the grout should be removed from the surface and replaced with a fresh layer. The tiles should be laid by placing the second one as close to the first one and moving it to receive a joint of proper width. The tiles should not be wet before laying! Press tiles and if need be strike with a rubber hammer against the bed so that the adhesive will adhere to at least 70% of surface of a tile. Tiles bigger than 30x30 cm, all tiles laid outside and in permanently wet and intensively used places should be laid so that the adhesive will adhere to the entire tile surface. In order to meet these requirements the adhesive should be also applied to the entire back of the tile with a thin layer of equal thickness, covering the concavities and convexities.</p> <p>The joint width should be chosen based on the tile size. Internal floors adopt the following: minimum 2mm - at the tile side length up to 10 cm, 2-6mm - using tiles of 10-25cm, 4-8 mm - using tiles of 25-30 cm. Before the adhesive dries, the possible grout residue should be removed from the joints, and the tiles should be washed with water.</p>
Application conditions:	<p>Apply in temperatures from +5 °C do +25 °C. These temperatures apply to air, groundwork and product temperature. All groundworks should be load-bearing, tight, stable, cleared and, if necessary, primed with EXPERT 6 or GRUNTOLIT-W 301. Prime poor-quality groundworks with EXPERT 5 – deep-penetration primer. Smooth substrates that require increased adhesion are recommended to be primed with GRUNT CONTACT 307.</p>
Instructions:	<p>Do not apply on gypsum plasters, plasterboards, screeds with floor heating and anhydrite screeds, as well as for gres tiles.</p> <p>For tiles with 30cm in side length, apply an adhesive offering increased elasticity.</p> <p>Avoid contact with skin and protect eyes. Detailed guidelines are included in the material safety data sheet.</p>
Storage:	<p>Up to 12 months from the date of manufacture, in dry places and in intact packaging</p>
General information:	<p>This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing.</p> <p>All technical data is given for the temperature of 20 degrees Celsius. These temperatures apply to air, bed and embedded material.</p>