




HASIT Reinforcement fabric White HDP


Glass fibre reinforcement fabric

Areas of application: Alkali-resistant, high-quality textile glass mesh for the reinforcement of thermal insulation plaster systems, TICS systems and for renovating fillers. Surface weight: approx. 215 g/m², Type: 123
Surface weight: approx. 215 g/m²
Type: 123

- Properties:**
- Alkali-resistant
 - Good plaster adhesion
 - PVC-free
 - Non-displaceable
 - Plasticizer-free

Application procedure:



Technical data		
Item no.	200005715	2000092614
EAN	8588004998032	8588004998124
Customs Tariff No.	70196600	
Packaging type		
Quantity per unit	50 m ² /unit	55 m ² /unit
Unit per pallet	20 unit/Pal.	
Length	50 m	
Width	100 cm	110 cm
Colour	White	
Consumption	approx. 1.1 lfm/m ²	
Mesh size	6 x 6 mm	
Weight per unit area done	0.215 kg/m ²	
Tensile strength warp (initial value)	2,700 N/5 cm	
Tensile strength warp (residual value)	1,400 N/5 cm	
Tensile strength weft (initial value)	2,700 N/5 cm	
Tensile strength weft (residual value)	1,400 N/5 cm	
Approval	Z-33.41-1218 Z-33.43-1219 Z-33.44-1220 Z-33.47-1503 Z-33.43-942 Z-33.47-660	

- Material base:**
- Textile glass mesh with high-quality impregnation.
 - Material class: E-glass

Application conditions: During the processing and drying phase, the temperature of the surrounding environment and of the substrate must not drop below +5 °C.



HASIT Reinforcement fabric White HDP

Glass fibre reinforcement fabric

Application procedure:	<p>Press the reinforcing mesh into the mortar bed, overlap by at least 10 cm in the area of the joints and smooth over with a trowel. If necessary, level with a smoothing trowel.</p> <p>Fiberglass mesh can be pressed into an already applied reinforcing layer.</p> <p>Fabric joints must be overlapped by 10 cm. The black edge strips serve as overlap markings for this purpose.</p> <p>At building openings (windows, doors), a HASIT fabric corner arrow or diagonal reinforcement with fabric strips (minimum size 20x40 cm) must be applied. This must be embedded before the surface reinforcement is applied.</p> <p>If the mesh is etched e.g. in the anchor area, it is necessary to press in an additional mess strip over the overlapping point.</p> <p>Mesh should be protected from mechanical damage (removal of layers with a spoon).</p>
Packaging:	Sheets in recyclable PE.
Storage:	Dry, protect from humidity and UV radiation (sun, light). Storing 12 months.
Hazard statements:	Please refer to our separate safety data sheets for detailed safety instructions. Read through these before use.
General information:	<p>This technical data sheet substitutes and annuls the previous editions of the same.</p> <p>The data is processed carefully and conscientiously, however they do not provide a warranty for the accuracy and completeness of the same, nor are they responsible for future decisions of users. These data itself is not based on legal relations or other additional obligations. These data do not release the customer from the obligation to check whether the product is suitable for its intended purpose.</p> <p>Our products, as well as all raw materials contained in them, are subject to continuous monitoring in order to guarantee consistent quality.</p> <p>If you have further questions, please contact your sales advisor or specialist retailer.</p> <p>The current status of our technical bulletins can be found on our website or can be requested in the responsible office.</p>