

Fixit Dämmputzmatrix

Standzeiten Dämmputze für die Planung

Anwurf	Fixit 211	CC Vorspritz	Fixit 670	Fixit 462	Fixit 210	Welnet
Standzeiten	5 Tage	1 – 3 Tage	3 Wochen	1 Tag/mm	10 Tage	sofort
Backstein	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC		Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC
Beton	Fixit 222 242 CC / 267 CC			Fixit 222		Fixit 222 242 CC / 267 CC
Bruchstein	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC		Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC
Stampfbeton	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC		Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC
Sandstein		Fixit 222 242 CC / 267 CC			Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC
Fachwerk*	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC		Fixit 222 242 CC / 267 CC	Fixit 222 242 CC / 267 CC
Kalkputz		Fixit 222 242 CC / 267 CC		Fixit 222		Fixit 222 242 CC / 267 CC
Zementputz	Fixit 222 242 CC / 267 CC			Fixit 222		Fixit 222 242 CC / 267 CC

*Holz abdecken mit Dachpappe

Netzeinbettung	Fixit 222	267 CalceClima® Thermo	242 CalceClima® Thermo
8 x 8 mm	Fixit 223	Fixit 462	Fixit 427
Standzeiten zur Weiterbeschichtung	10 Tage	1 Tag/mm	10 Tage
kein Netz notwendig		bis 4cm	

Trocknungszeiten Dämmputze			
Dämmdicke	Fixit 222	267 CalceClima® Thermo	242 CalceClima® Thermo
3 cm	21 Tage	14 Tage	21 Tage
4 cm	21 Tage	20 Tage	21 Tage
5 cm	21 Tage	25 Tage	21 Tage
6 cm	21 Tage	30 Tage	21 Tage
7 cm	23 Tage	35 Tage	23 Tage
8 cm	26 Tage	40 Tage	26 Tage
9 cm	30 Tage	45 Tage	30 Tage
10 cm	33 Tage	50 Tage	33 Tage
11 cm	36 Tage	55 Tage	36 Tage
12 cm	40 Tage	60 Tage	40 Tage

Auftragsstärke	Fixit 222	267 CalceClima® Thermo	242 CalceClima® Thermo
Minimum	30 mm	30 mm	20 mm
Maximum	150 mm	120 mm	100 mm