

TECHNICAL DATA SHEET

SILIKATYNK 020

Silicate render



Areas of application

Ready to use, dyed plaster grout on the basis of potassium waterglass. Thin-layer finishing coats for indoor and outdoor applications. Incorporated in the TURBO-SA and TURBO-WSA thermal insulation systems by KREISEL. Plaster with a structure of 2 mm is also suitable for mechanical use. After drying, the grout creates a flexible, mold-resistant and durable plaster layer.


Properties

- Waterproof
- Frost-resistant
- UV resistant
- Resistant to biological aggression
- Highly weather-resistant
- Vapor-permeable
- Crystalline tie with the groundwork

Application procedure



Technical data

Item number	17326	17403
Packaging		
Quantity per unit	25 kg/unit	
Unit per pallet	33 unit/Pal.	
Grain size	0-1,5 mm	0-2 mm
Plaster structure	Dashed	
Colour	coloured	
Consumption	2,3 kg/m ²	3,5 kg/m ²
Hardening time	approx. 48 h	
sd-value	< 0,26 m	
Processing time	20 min	

SILIKATYNK 020

Silicate render

Material base

- Potassium water glass
- Mineral fillers
- Pigments
- Polymer dispersion
- Additives

Application conditions

Apply at temperatures from +5 °C to +25 °C, these temperatures apply to air, bed and product. All substrates shall be bearing, compact, stable, even and clean

Surface

Before applying the plaster, all groundworks must be primed with TYNKOLIT-T 330 Symptoms of biological aggression should be eliminated. Highly absorbent, dusty substrates should be primed with GRUNTOLIT-W 301 or EXPERT 6 before applying a TYNKOLIT-type primer. Groundwork must be cleared from dust, grease, anti-adhesive solutions, paint residue, mold, algae, moss, etc., free from cracks and saline efflorescence.

Reinforcing layer in the thermal insulation system: Prime with TYNKOLIT-U 340

Cement-lime plaster: Prime with TYNKOLIT-U 340

Gypsum plaster: Prime with TYNKOLIT-U 340

Gypsum plasterboards: Prime with TYNKOLIT-U 340

Concrete, reinforced concrete: Prime with TYNKOLIT-U 340

Preparation

Ready-to-use product. Do not dilute with water or mix with other materials. Mix thoroughly before use. Before applying, check if the color matches your order. Products marked with a sticker with the inscription: Base B or Base C or Base D are semi-finished products intended for further coloring. In order to obtain appropriate color intensity, good coverage and avoid color differences, they require pigmentation. Using them without pigments is not allowed. Slight color deviations from the sample are possible. For large areas and critical color tones, a test should be carried out after drying to check the color match of the paint. Under real conditions, due to the drying rate, the type of substrate and the application technique, these colours may slightly differ from

those shown in the colour charts.

Application procedure

Apply the plaster on the substrate with a trowel of stainless steel to be as thick as a grain, afterwards - excess must be removed with the same trowel. Finally, rub with a trowel of plastic While performing works and during drying process, protect from frost, rainfalls, too high temperatures and strong winds. The use of scaffolding covers is recommended In order to balance the color and structure of the plasters, it is recommended not to empty the bucket completely with the plaster mass during application, but to add half of it with fresh mass from the new bucket after emptying and to mix both parts carefully

Use the entire set of products in the thermal insulation system. One one surface, apply plaster from one production batch only. Process a surface in a continuous manner, applying the wet on wet method to avoid visible lines.

Properly dyed substrate shall be recommended under colour plasters, especially plasters with scratched structure. Falling fogs, when the coating is not dry enough, work as a raining drizzle and may cause patches and discolourations. Intense colours with light reflectance value $Y < 25\%$ should be used on small surfaces of facades. Their use on entire surfaces results in accelerated ageing of coating due to intense heating and high thermal stress. Clean tools with clean water immediately after finishing work. In the case of mechanical application, apply on the earlier prepared bed using a unit or gun until the bed is appropriately covered with the plastering mass. Way of application (in strips or using circular movements) is dependent on the type of unit. For spray application, a machine such as the Graco RTX 5500 can be used, with a 4.5 mm nozzle (for 1.5 mm render grain size) or a 6.0 mm nozzle (for 2.0 mm render grain size). Apply at a pressure of 2–3 bar.

Hazard statements

Please, refer to the Safety Data Sheet for detailed guidance. Please, read and understand its contents before use.

Storage

Up to 12 months from production date in sealed packaging and at temperatures, ranging from +5 °C to +25 °C, far from sources of heat and frost.

SILIKATYNK 020

Silicate render

Label

