

TECHNICAL DATA SHEET

HASIT 730

LITHIN® fantasy plaster




Areas of application

Factory-mixed fine plaster mortar according to DIN 18557, mortar group P I according to DIN V 18550 or category CR-CS I-WC2 according to DIN EN 998-1. Mineral, hydrophobic structural finishing plaster for outdoor use and for decorative design indoors on mineral base plasters and fabric fillers, plasterboard and fibre cement boards, etc. As modeling plaster for creating fantasy structures such as Waschel structures or structures with trowel marks as well as smooth-coated fine plaster structures. Low-chromate dry mortar according to Directive 2003/53/EC.


Properties

- Mineral, ecological
- High open diffusion
- Easy processing
- Can be freely structured

Application procedure



Technical data

Item number	2000006255	2000007171	2000007254	2000007259
EAN	4038502164384	4038502104915	4038502161178	4038502161185
Customs Tariff No.	32149000			
Packaging				
Quantity per unit	30 kg/unit			
Unit per pallet	42 unit/Pal.			
Grain size		0-1 mm	0-2 mm	0-3 mm
Colour	customizable	Natural white		
Colour selection	Limited			
Consumption		approx. 1,4 kg/m ² /mm	approx. 1,5 kg/m ² /mm	
Water consumption	approx. 7,5 L/unit			
Reaction to fire	A1			

HASIT 730

LITHIN® fantasy plaster

Item number	2000006255	2000007171	2000007254	2000007259
Water absorption	< 0,2 kg/m ² *min0,5			
Water vapour diffusion	≤ 20			
Vapour diffusion openness	High open diffusion			
Compressive strength	approx. 1,5 N/mm ² (28 d) EN 1015-11			
Thermal conductivity	0,61 W/mK for P=50% 0,66 W/mK for P=90%			
Mortar class	Fine plaster mortar CR - CS I - WC2 EN 998-1 PI DIN 18550			
pH-value	12			
Layer thickness	0-3 mm			
Specific heat capacity	approx. 1 J/kg K			
Dry density	< 1400 kg/m ³			
Substrate temperature	5-30 °C			
Packaging	In recyclable paper bags.			

Material base

- Air lime
- Mineral
- Raw white, high-quality sands
- White cement

Application conditions

Until completely dry, protect against frost and rapid drying (direct sunlight, strong air currents and subsequent moisture or rain).

Surface

The surface has to be dry, without dust, unfrosted, absorptive, flat, sufficiently rough and bearing as well as without efflorescence and release agents creating a film (such as formwork oil and similar). Lime/cement-based TICS base plasters must be applied in the specified layer thickness according to the applicable guidelines and be dried (7–10 days – longer in damp, cold weather). Gypsum base plasters must be sufficiently strong, dry and set.

Lime-cement base plasters can be plastered after hardening.

Lime base plasters: Applicable after sufficient drying of the plaster base

Lime-cement undercoat plasters: When the plaster base has sufficiently dried, apply HASIT 251 RENOSTAR® renovation filler and a reinforcement layer with HASIT adhesive and reinforcing mortar, e.g. HASIT DIEPLAST 804/860. To equalize the substrate's absorption behaviour and thus achieve uniform colouring of the fine plaster as well as to improve adhesion and additional hydrophobicity, HASIT PLASTER BASE UNI or HASIT PLASTER BASE PREMIUM is recommended.

Lightweight base plasters: When the plaster base has sufficiently dried, apply HASIT 251 RENOSTAR® renovation filler and a reinforcement layer with HASIT adhesive and reinforcing mortar, e.g. HASIT DIEPLAST 804/860. To equalize the substrate's absorption behaviour and thus achieve uniform colouring of the fine plaster as well as to improve adhesion and additional hydrophobicity, HASIT PLASTER BASE UNI or HASIT PLASTER BASE PREMIUM is recommended.

Thermal insulation plasters: When the plaster base has sufficiently dried, apply HASIT 251 RENOSTAR® renovation filler and a reinforcement layer with HASIT adhesive and reinforcing mortar, e.g. HASIT DIEPLAST 804/860. To equalize the substrate's absorption behaviour and thus achieve uniform colouring of the fine plaster as well as to improve adhesion and additional hydrophobicity, HASIT

HASIT 730

LITHIN® fantasy plaster

PLASTER BASE UNI or HASIT PLASTER BASE PREMIUM is recommended.

Concrete: On adhesive fillers with HASIT 605 adhesive and reinforcing mortar. Before coating, prime with HASIT PLASTER BASE PREMIUM.

Thermal-insulation systems, thermal-insulation plasters, elastic surfaces: Do not use on the following surfaces. Mineral old plaster without coating: On renovation filler HASIT 251 RENOSTAR®. To equalize the substrate's absorption behaviour and thus achieve uniform colouring of the fine plaster as well as to improve adhesion and additional hydrophobicity, HASIT PLASTER BASE UNI or HASIT PLASTER BASE PREMIUM is recommended.

Old plaster with mineral coating: On renovation filler HASIT 251 RENOSTAR®. To equalize the substrate's absorption behaviour and thus achieve uniform colouring of the fine plaster as well as to improve adhesion and additional hydrophobicity, HASIT PLASTER BASE UNI or HASIT PLASTER BASE PREMIUM is recommended.

Organic old plasters: On renovation filler HASIT 251 RENOSTAR®. To equalize the substrate's absorption behaviour and thus achieve uniform colouring of the fine plaster as well as to improve adhesion and additional hydrophobicity, HASIT PLASTER BASE UNI or HASIT PLASTER BASE PREMIUM is recommended.

Dry undercoat plasters which contain gypsum: Pretreatment using HASIT GIKA PUTZGRUND.

Gypsum plasterboards: Pre-fill the entire surface with HASIT PF 130 TOP FILL wall and joint filler and, after joint filling, pre-treat with HASIT GIKA PUTZGRUND.

plaster-paper fibre wallboards (e.g. Fermacell): On inflexible building boards and substrate pretreatments with HASIT GIKA PLASTER BASE

Surface pre-treatment

The plaster base must be inspected and prepared in accordance with DIN 18350. If there are different materials in the plaster base (e.g. due to repairs), it is advisable to level the entire surface with a fabric filler in order to achieve a level and uniformly absorbent substrate. Do not start with the finishing coat until the base coat has dried uniformly, otherwise colour differences may occur. Pre-fill plasterboards completely with HASIT PF 130 TOP FILL joint and wall filler or pre-coat with HASIT GIKA PUTZGRUND undiluted and evenly covering. Pre-fill smooth concrete surfaces with appropriate HASIT construction adhesive/filler. Please also note the applicable national regulations, the BFS and Fachgemeinschaft Kunstharzputze e.V. information sheets and VDPM/IWM guidelines.

Preparation

Provide clear water in a clean container and mix the dry mortar homogeneously using a powerful stirrer (rotor agitator). The water temperature must not exceed +25 °C. Do not mix for less than 3 minutes. After mixing, let rest for about 10 minutes (maturation time). Then mix again briefly. During processing mix the final plaster quite often in order to avoid granulation. If possible, mix the entire quantity for one side of the façade at once (at least 3 bags). Never empty the trough completely, always add mixture.

Application procedure

Apply evenly (without nests or seams) using a clean, rust-proof steel trowel/smoothing trowel in grain size. Application as a sprayed plaster: Apply (structure) using a suitable plaster spray machine.

When using a machine, it is important to ensure that a lime slurry is prepared and a 35 mm pump outlet piece and appropriate hoses are available. Ensure that the hose couplings are tight and the maximum hose length is 15 metres.

Structuring as a textured plaster: Using a suitable rubbing board (styrofoam/plastic trowel), create the desired structure on the not yet hardened plaster applying circular movements.

Structuring using a Waschel plaster: This is produced by irregular spreading of the freshly applied plaster mortar with a ceiling brush (Waschel).

Structuring using a plaster with trowel strokes (also plaster with trowel marks): This is produced by spreading/plastering the freshly applied plaster mortar in a fan-shaped or scale-shaped pattern.

Pay attention to structuring on time.

Backlog (untreated) material on tools can affect the structuring and cause an uneven structural image.

After each use the tools are to be cleaned thoroughly and properly.

Ensure adequate ventilation for drying.

The fresh mixture should be processed for 2 hours.

Do not mix with other materials.

After use, clean the tool thoroughly with water.

Due to the use of natural raw materials, slight colour differences are possible. For subsequent deliveries, the colour tone must be verified before installation. With coloured finishing plasters, only use paint from one delivery or colour batch on adjacent surfaces. When reordering, reference must always be made to the first order.

Processing in changing weather conditions can lead to

HASIT 730

LITHIN® fantasy plaster

colour differences. Coloured plasters can have a shorter processing time than white ones.
Fresh top coats must be protected with suitable facade protection netting from adverse weather conditions such as frost, direct sunlight, wind, rain, etc., until completely dry.

Hazard statements

Please, refer to the Safety Data Sheet for detailed guidance. Please, read and understand its contents before use.

Storage

Indoor storage in cold freezing-free conditions, in well-closed packages. Protect from direct sunlight. Can be stored for at least 12 months.

Certificates



Label



General information

This data sheet invalidates all previous editions. The information in this technical data sheet corresponds to our current knowledge and practical application experience. The information has been prepared carefully and conscientiously, but without guarantee for accuracy, timeliness, and completeness, and without liability for further decisions of the user. The information alone does not establish any legal relationship or other ancillary obligations. They do not absolve the customer from the obligation to independently verify the suitability of the product for the intended use. Technical values refer to the base products. Deviations from the technical specifications may occur due

to tinting and coloring. The specified values are average values. For coating substrates not described here, it is necessary to consult with us. Color tones may slightly vary in repeat orders or compared to the color chart, if necessary, a sample area should be created on-site. Information on drying and waiting times applies under laboratory conditions (+20°C/65% relative humidity) and may change depending on the site situation. All technical data listed in this product specification has been determined under laboratory conditions. Please follow the updated BFS data sheets, the data sheets issued by the Fachgemeinschaft Kunstharzputze e.V., the guidelines of the WDVS professional association and the IWM guidelines. If the HBW (luminosity value) is < 20 % of the final coating (finished facade), the HASIT SycoTec® system must be applied. In the case of fine plasters, some colour differences and efflorescences can occur due to high air humidity and low temperatures that delay the setting processor or when rain falls on a freshly plastered façade. In order to achieve visually flawless, uniformly coloured façades, an additional levelling coat must be applied, with the exception of scratch plasters, according to the Industrieverband Werkmörtel information sheet, but a coating system is recommended. Do not use on horizontal surfaces exposed to water (e.g. protruding plinths). Sample boards, colour cards, etc. are to be regarded as templates only. Colours may vary depending on the drying and the structure of the finishing plaster. Different processing methods can also lead to structural differences. In order to prevent colour deviations, reference must always be made to the delivered sample for orders based on samplings, and to the initial delivery in the case of reorders.