



ADHESIVE FOR FACADE STONE 102K

Frost-proof adhesive for ceramic and terracotta tiles

Areas of application: Intended for pasting claddings of artificial facade stone as well as for ceramic tiles, and other elements inside and outside a building.

- Properties:**
- Frost-resistant
 - Waterproof
 - Thin layer
 - C1T class
 - For facade stone
 - For cement tiles

Application procedure:



Technical data	
Item no.	34469
Packaging type	
Quantity per unit	12 kg
Unit per pallet	33 Pcs/pallet
Consumption	approx. 1.5 kg/m ² /mm
Drying time	from 24 to 48 hours
Application time	2 h
Layer thickness	1 - 5 mm
Soluble chromium VI content	≤ 0.0002 %
Amount of water required	approx. 2.8 l/bucket
Possibilities to enter	approx. 24 h
Groutable	after 48 hours
Adhesion to (Concrete)	≥ 0.5 N/mm ²
Correction possibility	approx. 10 min
Adhesive open time	10 min

The product conforms to: • EN 12004+A1

- Material base:**
- Mineral fillers
 - Modifying supplements
 - Portland cement

Surface: All substrates must be load bearing and seasoned, if necessary, primed with GRUNTOLIT-W 301. Remove all unstable grouts and coats. Plasters and cement screeds must be at least 4 weeks old, gypsum plasters and anhydrite screeds must be at least 2 weeks old. Grind and vacuum anhydrite screed. Concrete groundwork must be at least 6 months old.

Types of substrate:

Cement-lime plaster: Prime with GRUNTOLIT-W 301 or EXPERT 6
Gypsum plasters: Prime with GRUNTOLIT-SG 302 or EXPERT 5
Concrete, reinforced concrete: Depending on absorptivity - prime with GRUNTOLIT-W 301 or GRUNTEM KONTAKTOWYM 307.
Bricks and ceramic CMUs: Prime with GRUNTOLIT-W 301 or EXPERT 6
Autoclaved aerated concrete elements: Prime with GRUNTOLIT-SG 302 or EXPERT 5



ADHESIVE FOR FACADE STONE 102K

Frost-proof adhesive for ceramic and terracotta tiles

Preparation:	<p>Pour the dry mix gradually to a container with a sufficient amount of clean, cool water, mixing manually or using a low-speed mixer to produce homogenous, lump-free mass. Leave to mature for 5 minutes, and then mix again.</p> <p>If there is a need to use a part of the packaging, the entire dry compound must be carefully stirred because during transport components could be separated.</p> <p>Do not mix the hardened grouting mixture again.</p>
Application procedure:	<p>Apply the prepared mortar onto the steel trowel and firmly spread a thin layer across the bed using the straight edge. The next step is to apply a thicker mortar layer and spread it using the notched edge of the trowel at an angle of 45-60 degrees to the bed. The area covered with the mortar should be adjusted to the tiles laying abilities not to exceed the open drying time of the adhesive. It can be verified by touching the grout with a finger, if no adhesion occurs, the open drying time was exceeded and the grout should be removed from the surface and replaced with a fresh layer. The tiles should be laid by placing the second one as close to the first one and moving it to receive a joint of proper width. The tiles should not be wet before laying! Press tiles and if need be strike with a rubber hammer against the bed so that the adhesive will adhere to at least 70% of surface of a tile. Tiles bigger than 30x30 cm, all tiles laid outside and in permanently wet and intensively used places should be laid so that the adhesive will adhere to the entire tile surface. In order to meet these requirements the adhesive should be also applied to the entire back of the tile with a thin layer of equal thickness, covering the concavities and convexities.</p> <p>The joint width should be chosen based on the tile size. Internal floors adopt the following: minimum 2mm - at the tile side length up to 10 cm, 2-6mm - using tiles of 10-25cm, 4-8 mm - using tiles of 25-30 cm. Before the adhesive dries, the possible grout residue should be removed from the joints, and the tiles should be washed with water.</p>
Application conditions:	<p>Apply in temperatures from +5 °C to +25 °C, these temperature refer to air, groundwork and product temperature.</p>
Instructions:	<p>Do not apply on screeds with floor heating and anhydrite screed, as well as for gres tiles. Read the safety data sheet before use.</p>
Storage:	<p>Up to 12 months from the date of manufacture, in dry places and in intact packaging</p>
General information:	<p>This product data sheet replaces all its previous versions. The information, included in this technical card, represents our current knowledge and practical experience. This is general information only which shall not obligate the manufacturer to take any responsibility either for workmanship or for the manner of use. For there may be differences and specific execution conditions. The product shall be applied in accordance with required technical knowledge and OHS rules. Avoid contact with skin and protect eyes. In case of contact with eyes, rinse them up with a large quantity of clean water and consult a doctor. It shall be recommended to use gloves, safety goggles and protective clothing.</p> <p>All technical data is given for the temperature of 20 degrees Celsius. These temperatures apply to air, bed and embedded material.</p>